


AMENDMENTS TO THE CLAIMS


Listing of claims:

This listing of claims replaces all prior versions and listings of claims in the application.


1. (Withdrawn) An imide resin, comprising: a repeating unit represented by General Formula (1); a repeating unit represented by General Formula (2); and a repeating unit represented by General Formula (3), wherein an orientation birefringence of the imide resin ranges from -0.1×10^{-3} to 0.1×10^{-3} ,



where each of R^1 and R^2 independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^3 represents a hydrogen atom, an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where each of R^4 and R^5 independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^6 represents an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where R^7 represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^8 represents an aryl group having 6 to 10 carbon atoms.

2. (Withdrawn) The imide resin as set forth in claim 1, wherein the orientation birefringence ranges from -0.01×10^{-3} to 0.01×10^{-3} .

3. (Withdrawn) A polarizer-protective film as set forth in claim 1, wherein a molar ratio of the repeating unit represented by General Formula (1) and the repeating unit represented by

General Formula (3) ranges from 1.0:1.0 to 4.0:1.0.

4. (Withdrawn) The imide resin as set forth in claim 1, wherein a photoelastic coefficient is not more than $10 \times 10^{-12} \text{ m}^2/\text{N}$.

5. (Withdrawn) The imide resin as set forth in claim 1, wherein a glass transition temperature is not less than 120° C.


6. (Withdrawn) The imide resin as set forth in claim 1, being produced on the basis of a method in which a methyl methacrylate-styrene copolymer is treated with an imidization agent in the absence of a solvent.

7. (Withdrawn) The imide resin as set forth in claim 1, being produced on the basis of a method in which a methyl methacrylate-styrene copolymer is treated with an imidization agent in the presence of a solvent.


8. (Withdrawn) An optical resin composition, comprising as a main component the imide resin as set forth in any one of claims 1 to 7.

9. (Withdrawn) A molded product, comprising the optical resin composition as set forth in claim 8.


10. (Withdrawn) An imide resin, comprising: a repeating unit represented by General Formula (1); a repeating unit represented by General Formula (2); and a repeating unit represented by General Formula (3), wherein the imide resin has a negative orientation birefringence,



where each of R¹ and R² independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R³ represents a hydrogen atom, an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where each of R^4 and R^5 independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^6 represents an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where R^7 represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^8 represents an aryl group having 6 to 10 carbon atoms.

11. (Withdrawn) The imide resin as set forth in claim 10, wherein the orientation birefringence is not more than -0.15×10^{-3} .

12. (Withdrawn) The imide resin as set forth in claim 10, wherein a photoelastic coefficient is not more than $10 \times 10^{-12} \text{ m}^2/\text{N}$.

13. (Withdrawn) The imide resin as set forth in claim 10, wherein a glass transition temperature is not less than 120°C .


14. (Withdrawn) The imide resin as set forth in claim 10, being produced on the basis of a method in which a methyl methacrylate-styrene copolymer is treated with an imidization agent in the absence of a solvent.

15. (Withdrawn) The imide resin as set forth in claim 10, being produced on the basis of a method in which a methyl methacrylate-styrene copolymer is treated with an imidization agent in the presence of a solvent.

16. (Withdrawn) An optical resin composition, comprising as a main component the imide resin as set forth in any one of claims 10 to 15.


17. (Withdrawn) A molded product, comprising the optical resin composition as set forth in claim 16.

18. (Withdrawn) An imide resin, comprising: a repeating unit represented by General Formula (1); a repeating unit represented by General Formula (2); and a repeating unit represented by General Formula (3), wherein a melt viscosity of the imide resin ranges from 1000 to 50000 poise,



where each of R^1 and R^2 independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^3 represents a hydrogen atom, an alkyl group having 1 to 18

carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where each of R^4 and R^5 independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^6 represents an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where R^7 represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^8 represents an aryl group having 6 to 10 carbon atoms.

19. (Withdrawn) The imide resin as set forth in claim 18, having positive orientation birefringence.

20. (Withdrawn) The imide resin as set forth in claim 18, wherein the orientation birefringence is not less than 0.15×10^{-3} .

21. (Withdrawn) The imide resin as set forth in claim 18, wherein a photoelastic coefficient is not more than $10 \times 10^{-12} \text{m}^2/\text{N}$.

22. (Withdrawn) The imide resin as set forth in claim 18, wherein a glass transition temperature is not less than 120°C.

23. (Withdrawn) The imide resin as set forth in claim 18, being produced on the basis of a method in which a methyl methacrylate-styrene copolymer is treated with an imidization agent in the absence of a solvent.

24. (Withdrawn) The imide resin as set forth in claim 18, being produced on the basis of a method in which a methyl methacrylate-styrene copolymer is treated with an imidization agent in the presence of a solvent.


25. (Withdrawn) An optical resin composition, comprising as a main component the imide resin as set forth in any one of claims 18 to 24.

26. (Withdrawn) A molded product, comprising the optical resin composition as set forth in claim 25.


27. (Currently Amended) A polarizer-protective film, comprising an imide resin which includes: a repeating unit represented by General Formula (1); a repeating unit represented by General Formula (2); and a repeating unit represented by General Formula (3), wherein:

a content of the repeating unit represented by General Formula (3) ranges from 5 wt% to 50 wt% with respect to an amount of total repeating units of the imide resin; and


a thickness of the polarizer-protective film falls within a range from 20 μm to 300 μm ,



where each of R^1 and R^2 independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^3 represents a hydrogen atom, an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where each of R⁴ and R⁵ independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R⁶ represents an alkyl group having 1 carbon atom,



where R⁷ represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R⁸ represents an aryl group having 6 to 10 carbon atoms, [[and]]

wherein the imide resin does not include a repeating unit represented by General Formula (2) where R⁶ represents a hydrocarbon group having 2 or more carbon atoms,

wherein an orientation birefringence of the imide resin ranges from -0.1×10^{-3} to 0.1×10^{-3} , and

wherein a photoelastic coefficient of the imide resin is not more than $10 \times 10^{-12} \text{m}^2/\text{N}$.

28. (Cancelled).

29. (Original) The polarizer-protective film as set forth in claim 27, wherein an orientation birefringence of the imide resin ranges from -0.1×10^{-4} to 0.1×10^{-4} .

30. (Original) The polarizer-protective film as set forth in claim 27, wherein: in the imide resin, a molar ratio of the repeating unit represented by General Formula (1) and the repeating unit represented by General Formula (3) ranges from 1.0:1.0 to 4.0:1.0.

31. (Cancelled).


32. (Original) The polarizer-protective film as set forth in claim 27, wherein a glass transition temperature of the imide resin is not less than 120°C.

33. (Currently Amended) A polarization plate, comprising the polarizer-protective film as set forth in any one of claims 27 or 29 to 30 or 32 or 57.


34. (Withdrawn) A production method of a polarizer-protective film, comprising the steps of:

(i) making, into a film, an imide resin including a repeating unit represented by General Formula (1), a repeating unit represented by General Formula (2), and a repeating unit represented by General Formula (3); and


(ii) drawing the imide resin having been made into the film,



where each of R^1 and R^2 independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^3 represents a hydrogen atom, an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where each of R^4 and R^5 independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^6 represents an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where R^7 represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^8 represents an aryl group having 6 to 10 carbon atoms.


35. (Withdrawn) The polarizer-protective film as set forth in claim 34, wherein: in the imide resin, a molar ratio of the repeating unit represented by General Formula (1) and the repeating unit represented by General Formula (3) ranges from 1.0:1.0 to 4.0:1.0.

36. (Withdrawn) The production method as set forth in claim 34, wherein: in the step (i), the imide resin is made into the film on the basis of a melt extrusion method.


37. (Withdrawn) The production method as set forth in claim 34, wherein: in the step (i), the imide resin is made into the film on the basis of a solvent casting method.

38. (Withdrawn) The production method as set forth in claim 34, wherein: in the step (ii), biaxially stretching is carried out.

39. (Withdrawn) A retardation film, comprising an imide resin which includes: a repeating unit represented by General Formula (1); a repeating unit represented by General Formula (2); and a repeating unit represented by General Formula (3),



where each of R^1 and R^2 independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^3 represents a hydrogen atom, an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where each of R^4 and R^5 independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^6 represents an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where R^7 represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^8 represents an aryl group having 6 to 10 carbon atoms.

40. (Withdrawn) The retardation film as set forth in claim 39, wherein the imide resin has negative orientation birefringence.

41. (Withdrawn) The retardation film as set forth in claim 39, wherein an orientation birefringence of the imide resin is not more than -2×10^{-3} .

42. (Withdrawn) The retardation film as set forth in claim 39, wherein the imide resin includes 20 wt % to 50 wt % of the repeating unit represented by General Formula (3).


43. (Withdrawn) The retardation film as set forth in claim 39, wherein a photoelastic coefficient of the imide resin is not more than $10 \times 10^{-12} \text{m}^2/\text{N}$.

44. (Withdrawn) The retardation film as set forth in claim 39, wherein a glass transition temperature of the imide resin is not less than 120°C.


45. (Withdrawn) A production method of a retardation film, comprising the steps of:

(i) making, into a film, an imide resin including a repeating unit represented by General Formula (1), a repeating unit represented by General Formula (2), and a repeating unit represented by General Formula (3); and


(ii) drawing the imide resin having been made into the film,



where each of R^1 and R^2 independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^3 represents a hydrogen atom, an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where each of R^4 and R^5 independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^6 represents an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,




where R^7 represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^8 represents an aryl group having 6 to 10 carbon atoms.

46. (Withdrawn) The production method as set forth in claim 45, wherein: in the step (i), the imide resin is made into the film on the basis of a melt extrusion method.


47. (Withdrawn) The production method as set forth in claim 45, wherein: in the step (i), the imide resin is made into the film on the basis of a melt drawing method.

48. (Withdrawn) A method for producing an imide resin which includes a repeating unit represented by General Formula (1) and has substantially no orientation birefringence, said method comprising the step of:


(a) treating, with an imidization agent, a resin including a repeating unit represented by General Formula (2) and a repeating unit represented by General Formula (3) so that a quantity of the repeating unit represented by General Formula (3) is 15 wt % or more and 40 wt % or less,



where each of R¹ and R² independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R³ represents a hydrogen atom, an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where each of R⁴ and R⁵ independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R⁶ represents an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,




49. (Withdrawn) The method as set forth in claim 48, wherein: in the step (a), the resin is treated with the imidization agent so that a molar ratio of the repeating unit represented by General Formula (1) and the repeating unit represented by General Formula (3) ranges from 1.0:1.0 to 4.0:1.0.


$$\begin{array}{c} \text{R}^2 \quad \text{R}^2 \\ | \quad | \\ \text{---} \text{C} \text{---} \text{C} \text{---} \text{C} \text{---} \text{C} \text{---} \\ | \quad | \quad | \quad | \\ \text{R}^1 \quad \text{R}^1 \quad \text{R}^1 \quad \text{R}^1 \\ \text{O}=\text{C} \quad \text{N} \quad \text{C}=\text{O} \\ | \\ \text{R}^3 \end{array} \quad \dots (1)$$

where each of R¹ and R² independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R³ represents a hydrogen atom, an alkyl group having 1 to 18

carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where each of R^4 and R^5 independently represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^6 represents an alkyl group having 1 to 18 carbon atoms, a cycloalkyl group having 3 to 12 carbon atoms, or an aryl group having 6 to 10 carbon atoms,



where R^7 represents a hydrogen atom or an alkyl group having 1 to 8 carbon atoms, and R^8 represents an aryl group having 6 to 10 carbon atoms.

51. (Withdrawn) An imidized methacrylic resin composition, being transformed by treating, with an imidization agent, a methacrylic resin composition (C) obtained by copolymerizing a methacrylic ester polymer (A) in the presence of acrylic ester cross-linking elastic particles (B), wherein:

the methacrylic ester polymer (A) is a polymer obtained by polymerizing a monomer mixture including 50 to 99 wt % of methacrylic alkyl ester, 0 to 49 wt % of acrylic alkyl ester, and 1 to 50 wt % of an aromatic vinyl monomer, and

the acrylic ester cross-linking elastic particles (B) are a copolymer obtained by polymerizing a monomer mixture (b) including 50 to 100 wt % of acrylic alkyl ester and 50 to 0 wt % of methacrylic alkyl ester with a multifunctional monomer having two or more unconjugated double bonds.

52. (Withdrawn) The imidized methacrylic resin composition as set forth in claim 51, wherein an orientation birefringence of the imide resin ranges from -0.1×10^{-3} to 0.1×10^{-3} .

53. (Withdrawn) The imidized methacrylic resin composition as set forth in claim 51, wherein a glass transition temperature of the imide resin is not less than 120°C.

54. (Withdrawn) A molded product, comprising the imidized methacrylic resin composition as set forth in any one of claims 51 to 53.

55. (Withdrawn) A film, being obtained by molding the imidized methacrylic resin composition as set forth in any one of claims 51 to 53.

56. (Withdrawn) A laminate, being obtained by laminating the film as set forth in claim 55 on metal or plastic.

57. (Previously Presented) The polarizer-protective film as set forth in claim 27, wherein the content of the repeating unit represented by General Formula (3) ranges from 10 wt% to 40 wt% with respect to the amount of the total repeating units of the imide resin.

58. (Cancelled).

59. (Previously Presented) The polarizer-protective film as set forth in claim 27, wherein the polarizer-protective film is produced by a method including (i) a step for making the imide resin into a film and (ii) a step for biaxially stretching the film of the imide resin.